



# Technical Information

Issue: September 2015

## Product Name

85-601771-0 Flex Overprint varnish

## 1. Description / Application

High gloss UV curing flexo varnish applied by roller coater; flexo unit.

## 2. Product Safety

### Intended Use

Food packaging, pharma, or hygiene: **NO**

Only acceptable for food packaging if the processing conditions rule out the possibility of set-off in the reel or stack and the design of the final printed article ensures reliable functional barrier properties to migration. For further information, please refer to **Siegwerk’s Customer Guidance: Printing Inks for Food Packaging (“Know How”)** on <https://www.siegwerk.com/en/our-responsibility/product-responsibility/customer-communications/food-packaging-safety.html> in particular chapter 5. “The printer’s selection of ink” has to be observed.

## 3. Properties / Substrates

### Properties

- high reactive
- very fast and assured curing
- uniform wetting on printing inks
- good adhesion
- good abrasion resistance
- good chemical resistance

### Substrates

Adhesion, scratch- and scuff resistance, water resistance (wet scratch and wet scuff resistance), heat-sealing resistance and resistances to fats, acid or alkaline products, cosmetics, lotions, shampoos, alcohol, cleaning agent and solvents are normally obtained on standard label substrates. Suitability of each substrate has to be tested before print run.

In case of doubt, please contact in time our technical department.



#### 4. Printing and processing instructions

- Gloss level: high gloss
- Dry solid content: 100 %
- For printing on inks containing high amounts of waxes, a preliminary test is recommended.
- Be careful of possible penetration of the varnish into porous substrates, which can affect the above mentioned properties.

##### Guidelines for use

*Before the print job is started, new materials must be checked for compatibility with the planned overprinting varnish/inks combination, even if their suitability on a comparable type of the same substrate group is proved.*

*The test prints, especially on self-adhesive labels, have to be examined after die-punching (in particular at the edges) for adhesion, resistance to scratching and water (resistance to wet scratching and scuffing), resistance to the packaging contents and other job-specific requirements.*

*Due to possible different material shrinkage and other alterations, these examinations must be repeated after one day.*

*Consequently, for every new job in which printing is done on a known material, but with untested ink and printing combinations, the aforementioned tests have to be carried out as well.*

Please see also the information on the material safety datasheet.

##### Cleaning

The varnish can be removed from tools by using methoxypropanol.

#### 5. Shelf life

This varnish has under normal conditions a shelf life of **at least 12 months**. Within this period the product is usable in conformity with the indications of this data sheet.

Normal conditions mean:

- Storage in firmly closed, not yet tapped containers.
- Temperatures not exceeding 20°C for weeks or 25°C for days.
- Do not expose open containers to direct sunlight or strong light sources.

Because of the differences in materials for printing, processing conditions and test criteria this Technical Information can only be of an advisory nature. Our data reflect the latest state of our knowledge and are based on the characteristics established in the laboratory and on practical experience. Your own tests with the original materials under the respective conditions are indispensable. We disclaim any liability for applications for which this product is not foreseen.