



Technical Information

Issue: September 2015

Product Name

85-601799-1 39-8 Neutralizing varnish 1025

1. Description / Application

Flexo neutralizing varnish for in-line printing, curing with UV-light by radical mechanism.

Particularly suitable for paper- and synthetic self-adhesive label materials.

2. Product Safety

Intended Use

Food packaging, pharma, or hygiene: **NO**

Only acceptable for food packaging if the processing conditions rule out the possibility of set-off in the reel or stack and the design of the final printed article ensures reliable functional barrier properties to migration. For further information, please refer to **Siegwerk's Customer Guidance: Printing Inks for Food Packaging ("Know How")** on <https://www.siegwerk.com/en/our-responsibility/product-responsibility/customer-communications/food-packaging-safety.html> in particular chapter 5. "The printer's selection of ink" has to be observed.

3. Properties / Substrates

Properties

- good printability
- low viscosity
- suitable for paper- and synthetic label materials

Substrates

Adhesion, resistance to scratching and scuffing, water resistance (wet scratch and wet scuff resistance), heat-sealing resistance and resistances to fats, acid or alkaline products, cosmetics, lotions, shampoos, alcohol, cleaning agents and solvents are normally obtained on standard label substrates. Suitability of each substrate has to be tested before print run.

- Coated papers and cartons.
- In-line corona pre-treated polyethylene with a surface tension of min. 40- 45 mN/m.
- In-line corona pre-treated polypropylene with a surface tension of min. 42- 45 mN/m.

Other substrates after technical evaluation.

Special applications

This varnish is normally **not stampable or not overprintable with the thermal-transfer method.**

In case of doubt, please contact in time our technical department.



4. Printing and processing instructions

Application volume: 4 g/m² → anilox roller with at least 12 cm³/m².

A permanent neutralizing effect requires a very good curing of the varnish.

Guidelines for use

Before the print job is started, new materials must be checked for compatibility with the planned overprinting varnish/inks combination, even if their suitability on a comparable type of the same substrate group is proved. The test prints, especially on self-adhesive labels, have to be examined after die-punching (in particular at the edges) for adhesion, resistance to scratching and water (resistance to wet scratching and scuffing), resistance to the packaging contents and other job-specific requirements.

Due to possible different material shrinkage and other alterations, these examinations must be repeated after one day.

Levelling/printability, mechanical resistances (e.g. adhesion, folding resistance, punching resistance), resistance to water and the weather, and in particular the resistances to the packaged products, depend largely on the properties of the pre-printed inks. The latter is particularly applicable if the ink film on the punching edge is exposed, and hence subject to lateral attack.

Consequently, for every new job in which printing is done on a known material, but with untested ink and printing combinations, the aforementioned tests have to be carried out as well.

Optimum performance is achieved by using the following criteria in the selection of the printing inks:

- Preferably radical UV-Letterpress, UV-Offset, UV-Screen printing or UV-Flexo inks.
- Best possible adhesion and resistance to water on the substrate to be printed.
- Best possible resistance of the printing ink series used to the packaged product.
- Exclusion of specific shades which contain pigments with poor fastness to the specified packaging content e.g. poor light and weather fastness.

Please see also the information on the material safety datasheet.

Cleaning

The varnish can be removed from tools by using methoxypropanol.

5. Shelf life

This varnish has under normal conditions a shelf life of **at least 12 months**. Within this period the product is usable in conformity with the indications of this data sheet.

Normal conditions mean:

- Storage in firmly closed, not yet tapped containers.
- Temperatures not exceeding 20°C for weeks or 25°C for days.
- Do not expose open containers to direct sunlight or strong light sources.

Because of the differences in materials for printing, processing conditions and test criteria this Technical Information can only be of an advisory nature. Our data reflect the latest state of our knowledge and are based on the characteristics established in the laboratory and on practical experience. Your own tests with the original materials under the respective conditions are indispensable. We disclaim any liability for applications for which this product is not foreseen.